NC/PMC/PD/2018-19/BW-CB9 **Date: 20-08-2018**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-08-18	20-08-18	07	22500	520	23.11	**23.85**
	002	"	"	"	"	540	24.00	
	003	"	"	"	"	550	24.44	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231,

NC/PMC/PD/2018-19/BW-CB10

Date: 21-08-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-08-18	21-08-18	07	22500	545	24.22	**24.52**
	002	"	"	"	"	560	24.89	
	003	"	"	"	"	550	24.44	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NC/PMC/PD/2018-19/BW-CB11 Date: 23-08-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).

{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-08-18	23-08-18	07	22500	540	24.00	**23.93**
	002	"	"	"	"	525	23.33	
	003	"	"	"	"	550	24.44	

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187 EMAIL:newzen576@gmail.com

NC/PMC/PD/2018-19/BW-CB12 Date: 24-08-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-08-18	24-08-18	07	22500	535	23.78	**24.07**
	002	"	"	"	"	550	24.44	
	003	"	"	"	"	540	24.00	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231,

NC/PMC/PD/2018-19/BW-CB13 Date: 25-08-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-08-18	25-08-18	07	22500	545	24.22	**24.37**
	002	"	"	"	"	555	24.67	
	003	"	"	"	"	545	24.22	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231,

NC/PMC/PD/2018-19/BW-CB14 Date: 25-08-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-08-18	25-08-18	07	22500	550	24.44	**23.93**
	002	"	"	"	"	530	23.56	
	003	"	"	"	"	535	23.78	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NC/PMC/PD/2018-19/BW-CB7A Date: 06-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	09-08-18	06-09-18	28	22500	715	31.78	**32.15**
	002	"	"	"	"	730	32.44	
	003	"	"	"	"	725	32.22	

KIRAN. R
M.E; (Civil-Engg)

NC/PMC/PD/2018-19/BW-CB8A Date: 07-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	10-08-18	07-09-18	28	22500	740	32.89	**32.52**
	002	"	"	"	"	720	32.00	
	003	"	"	"	"	735	32.67	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187 EMAIL:newzen576@gmail.com

NC/PMC/PD/2018-19/BW-CB9A Date: 10-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-08-18	10-09-18	28	22500	730	32.44	**32.81**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	740	32.89	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187 EMAIL :newzen576@gmail.com

NC/PMC/PD/2018-19/BW-CB10A

Date: 11-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-08-18	11-09-18	28	22500	735	32.67	**32.44**
	002	"	"	"	"	725	32.22	
	003	"	"	"	"	730	32.44	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANTS BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187 EMAIL:newzen576@gmail.com

NC/PMC/PD/2018-19/BW-CB11A **Date: 14-09-2018**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-08-18	14-09-18	29	22500	750	33.33	**33.11**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	740	32.89	

Page No. 1/1,

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NC/PMC/PD/2018-19/BW-CB12A

Date: 14-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-08-18	14-09-18	28	22500	730	32.44	**32.96**
	002	"	"	"	"	750	33.33	
	003	"	"	"	"	745	33.11	

Page No. 1/1,

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NC/PMC/PD/2018-19/BW-CB13A

Date: 15-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-08-18	15-09-18	28	22500	735	32.67	**32.59**
	002	"	"	"	"	725	32.22	
	003	"	"	"	"	740	32.89	

KIRAN. R
M.E, (Civil-Engg)

NC/PMC/PD/2018-19/BW-CB14A Date: 15-09-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Drilling of Borewell and providing pump motor and laying pipeline in Ward No.05 surrounding area Byatarayanapura Sub Division.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Y.A. Dhanashekhar.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-08-18	15-09-18	28	22500	730	32.44	**33.04**
	002	"	"	"	"	755	33.56	
	003	"	"	"	"	745	33.11	

KIRAN, R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor